MR – MOISTURE GYPSUM BOARD

09 29 00/GC



Description

Gypsemna's MOISTURE RESISTANCE (MR – 9.5mm) Type C Gypsum Board is an interior gypsum board consisting of a solid set, Type C gypsum core enclosed in GREEN coloured face paper and a strong liner back paper. Gypsemna's MR Type C board features a specially formulated core providing moisture resistance when used in wet area. Long edges are slightly tapered, allowing joints to be reinforced and concealed with joint tape and joint compound. The face paper and the back paper are 100 percent recycled.



Basic Uses

The Gypsemna's MOISTURE RESISTANCE (MR – 9.5mm)

Type C Gypsum Board is used for interior walls and ceilings in all buildings categories applications requiring extended moisture resistance, this makes Gypsemna MOISTURE RESISTANCE an ideal choice as a moisture resistant substrate for use in wet areas such as kitchens and bathrooms, behind sinks and basins and in shower cubicles. Also designed as a substrate for ceramic tiles.



Advantages

- · Consistently high quality.
- Moisture Resistance.
- Uniformly flat, attractive appearance; no shadows.
- · High edge hardness.
- Uniform high-strength cores eliminate crumbling, cracking.
- Edge tapers consistent to form perfect joints.
- Excellent thermal barrier and sound attenuation qualities.
- · Green certified.
- Qualifies as a low-VOC



Technical Data

Physical Properties

Thickness, Nominal 9.5mm

Width, Nominal 1200mm

Length, Standard 2400mm, 3000mm

Weight, Nominal 8.0kg/m2 Edges TE, SE

Color Green Color

Fire-Resistance Characteristics ASTM E84

Core Type Type C

Combustibility Non-combustible Core

Surface Burning Characteristics Class A

Flame Spread 0

Smoke Development 15

Standards and References

- ASTM C1396 Product Standard Compliance

- ASTM C473 Standard Test Methods for

Physical Testing of Gypsum Panel Products

- ASTM C840 Standard Specification for

Application and Finishing of Gypsum Board

- ASTM E84 Standard Test Method for Surface

Burning Characteristics of Building Materials

- EN 520 F & D Standard for performance of gypsum

plasterboards

Get in touch

